Lithium ion Polymer (LP) Battery Individual Data Sheets

LP-623048 have a combination of high energy density, super light and ultra thin. It's a perfect power source solution for mobile phone (such as Nokia® 8210/8250), small PDAs and other handheld device.

Specifications

Nominal voltage		3.7V	Cut-off voltage		3.0V
Standard charge method		Charging the cell initially with constant current at 0.5C and then with constant voltage at 4.2V till charge current <0.05C			
Max. charge current		1C	Max. discharge current		1.5C
Standard charge		0.5C×5hrs	Rapid charge		1C ×2.5hrs
Operating temperature			°C		° F
		Charging	0℃ ~45℃		32°F ~ 113°F
		Discharging	-20°C ~60°C		-4°F ~ 140°F
		Storage	-20℃ ~45℃		-4°F ~ 113°F
Cycle Life	≥500 Cycles	s (@0.5C discharge, 23°C)	Self-discharge	f-discharge Residual capacity>90% (@2: °C, 30 days)	

Remark:

- ^{*1} @ 0.2C discharge, 23°C
- ^{*2} Impedance is measured at AC 1KHz after Standard Charge.
- ^{*3} Cell weight is the approximate value for reference.

Cell Dimension

	mm	inch
Length	$\textbf{48.0} \pm \textbf{0.5}$	1.89 ± 0.02
Width	30.0 ± 0.5	$\textbf{1.18} \pm \textbf{0.02}$
Thickness	Max. 6.40	Max. 0.25



